

ALPINE ARMORING'S BALLISTIC CHART

WEAPONS	SPECS			LEVEL					BULLETS			NUMBER OF SHOTS	
	TYPE	CALIBER (mm)	CLASS	STANAG	UL	ALPINE	NIJ	CEN	MASS (g)	MATERIAL	VELOCITY		
	38 Special	9 x 19	Handgun	—	1	A1	I,II,IIA	—	8.00	LCCJ	358 M/S	5	
	357 Magnum	9 x 33	Handgun	—	2	A2	I,IIA	B1 & B3	10.20	JSP	430 M/S	5	
	.44 Magnum	11 x 33	Handgun	—	3	A3	IIIA	B4	15.60	LWC	440 M/S	5	
	MP5	9 x 19	SMG	—	6	A4	IIIA	B2	8.00	LCCJ	427 M/S	5	
	Shotgun	12 Gauge	Shotgun	—	3 & 4	A 5 SG	IIIA	SG2	28.30	SLUG	503 M/S	3	
	Tokarev	7.62 x 25	Handgun	—	—	A5	IIIA	—	5.50	LCSJ	488 M/S	5	
	Kalashnikov (AK-47)	7.62 x 39	Assault Rifle	—	—	A6	III	B5	9.70	SCCJ	732 M/S	5	
	Kalashnikov (AK-47 Military)	7.62 x 39 API BZ	Assault Rifle	II	—	A7	—	B5+	11.70	SCCJ	774 M/S	5	
	M16/AR-15	5.56 x 45 NATO SS109 5.56 x 45 NATO Ball	Assault Rifle	I	7	A8	IV	B5	4.00	SCCJ LCCJ	900 M/S 833 M/S	3	
	Winchester .308	7.62 x 51	Rifle	I	7	A9	III	B6	10.90	LCCJ	810 M/S	5	
	Remington 700 SPS	7.62 x 63 AP (.30-06) 7.62 x 51AP (WC core)	High-Power Rifle	III	5 & 8	A10	IV	B7-	10.80 8.40	AP	869 M/S 930 M/S	5	
	Dragunov	7.62 x 54R B32 API	Sniper Rifle	III	—	A11	IV+	B7+	10.04	SCCJ	854 M/S	1	
	50 Cal	12.7 x 99	High-Power Rifle	IV	10	A12	—	—	2220.00	CJ	908 M/S	1	

"no one protects you better"



UL Underwriters Laboratory, 752
NIJ National Institute of Justice, 0108.01
CEN European Standard
STANAG NATO's Standard (STANAG 4569)
ALPINE Alpine Armoring's Certified Standard

LCCJ Lead Core Copper Jacket
JSP Jacketed Soft Point
LWC Lead Wad Cutter
LCSJ Lead Core Steel Jacket
SCCJ Steel Core Copper Jacket
AP Armor Piercing
SG Shotgun

Shots (5) 11.4 cm Square Pattern (Corners & Center)
Shots (3) 11.4 cm Triangular Pattern
Velocity Minimum Measured Velocity
NIJ Rating ... Levels I, II, IIA, & IIIA (based on 1 of 2 required calibers of ballistic threat)

